

Ref. No. : PDS-0605-EN

Version No.: 4

Updated Date: 10.09.18

PRODUCT DATA SHEET

BILAC UNDERCOAT WHITE

Product Description:

BILAC UNDERCOAT WHITE is an Oil-Modified Alkyd undercoat with a high opacity and high solids coating that will effectively hide the substrate and impart a good film build to the overall coating system. Widely used as an undercoat over timber and metal.

Physical Characteristics of Paint:

Colour : White Finish : Matt

Specific Gravity : 1.50 ± 0.05

Solid Content : 57 ± 2 by volume

Performance Characteristics:

- Quick-dry
- High opacity for easy coverage
- Promote good intercoating adhesion
- Economical & easy to use

Recommendation for Use:

Surface Preparation

The surface to be painted must be dry, clean and free from dirt, grease, oil and other contaminations. Exposed metal must be primed with NIPPON BILAC METAL RED OXIDE PRIMER (Ferrous metals) or NIPPON 1100 FAST DRYING PRIMER (Ferrous metals) and NIPPON VINILEX 120 ACTIVE PRIMER (non-ferrous metals).

Recommended No. of Coats : 1 coat

Recommended Film Thickness per

coat

: 40 microns for dry film 70 microns for wet film

Theoretical Coverage at

Recommended Film Thickness

: 14.3 m² / liter (for dry film thickness of 40 microns)

Theoretical Coverage = $\frac{\text{Volume Solid (\%)} \times 10}{\text{(m}^2/\text{liter)}}$ Dry Film Thickness (μ)

NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II,Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836346 – 3836349



BILAC UNDERCOAT WHITE

Practical Coverage : 11.4 m² / liter (for dry film thickness of 40 microns) (20% Loss Factor)

Note: This theoretical coverage rate has been calculated from the volume solid of the material and is related to the amount of coating applied onto a perfectly smooth surface without wastage. For a practical coverage rate, due allowance should be made for atmospheric conditions, surface roughness, geometry of the article being coated, the skill of applicator, method of application etc. when estimating quantities required for a particular job.

Application Data:

Application Methods : Brush, roller, compressed air spray and airless spray

Guiding Data for Spray : <u>Air Airless</u>

Delivery Pressure (kg/cm²) 3 - 4 140 - 170

Tip size at 60° angle 1.3 mm 0.015" - 0.017"

Thinning: Roller & Brush 10% maximum

Air Spray 25% maximum
Airless Spray 5% maximum

Thinner : NIPPON BILAC THINNER

Cleaning Solvent : NIPPON BILAC THINNER

Note: All equipment should be cleaned IMMEDIATELY with Thinner after use. For thinning, substitute thinners other than those approved or supplied by Nippon Paint may adversely affect the product performance and void product warranty whether expressed or implied.

Drying Time				
Temperature (Degree C)	Touch dry (minutes)	Hard dry (minutes)	Over coating interval (Hours)	
			<u>Min</u>	<u>Max</u>
5 °C	150	480	24	Extended
15 °C	90	240	8	Extended
25 °C	60	180	5	Extended
40 °C	30	120	3	Extended

The reading is for guidelines only. Actual drying time before recoating may be shorter or longer depending on the film thickness, humidity, temperature, ventilation and underlying painting system.

Standard Packing : 0.8 Liter & 3 Liters

NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II,Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836346 – 3836349



BILAC UNDERCOAT WHITE

Environmental Conditions during Application:

- 1. Do not apply when the relative humidity exceeds 85%. The temperature of the substrate to be painted must be 3°C higher than the dew point.
- 2. Do not apply at temperature below 7°C. If not, drying and overcoating time will be considerably extended.
- 3. During application of the paint, naked flame, welding operations and smoking should not be allowed and good ventilation is necessary.

Safety, Health and Environmental Information:

- 1. Flammable Liquid. Do not expose to heat, sparks or open flame.
- 2. Skin Contact: May cause moderate skin irritation. Avoid prolong contact with skin. Use solvent resistant glove. To remove splashes of paint from skin, use soap and water.
- 3. Inhalation: Respiratory irritation. Only used in well ventilated areas. Do not breathe vapor or spray paint. Respirator with organic vapor cartridges recommended.
- 4. Eye Contact: Cause severe eye irritation and blurred vision. Safety glasses / goggles with side shields recommended. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.
- 5. Ingestion: Harmful if swallowed. Keep away from drinks, food and out of reach of children. If swallowed, seek medical advice immediately and show the container or label.
- 6. In the event of an accident, contain and collect spillage using sand or earth or absorbent. Do not empty into drain or water courses.
- 7. Wastes and empty containers should be treated and disposed of in accordance with national and local regulations. Empty containers and packaging should be taken for recycling, recovery or disposal through a suitably qualified or licensed contractor.

<u>NOTE:</u> The information given applies to the product and its performance under specific test conditions. Due to the varied circumstances beyond our control under which the product may be applied, for specific application, please contact Nippon Paint Sales & Marketing Dept. We reserve the right to modify our product data sheet without further notice.

NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II,Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836346 – 3836349

