
PRODUCT DATA SHEET

NIPPON EP4 CLEAR SEALER**Product Description:**

NIPPON EP4 CLEAR SEALER is a two-pack, high gloss Polyamide Epoxy Finish for use on concrete, plaster, brick and most types of building boards and. It is recommended for non-immersion services.

Physical Characteristics of Paint:

Colour	: Transparent
Finish	: High Gloss
Specific Gravity	: 1.02 ± 0.05 (for Mixture of Base & Hardener)
Solid Content	: 58 ± 2 by volume (for Mixture of Base & Hardener)
Abrasion	: Good resistance to abrasion and mechanical damage
Adhesion	: Excellent on correctly prepared surfaces
Temperature	: Dry service temperature range up to 100°C

Recommendation for Use:**Surface Preparation****Masonry and Cement Concrete Surface**

Moisture Content must be below 6% checked by Sovereign Moisture Meter. Unstable matter such as powder, old paint film, dirt and loose plaster should be removed by high pressure water jet washing or mechanical means such as power brush or scraper whichever is suitable. High pressure water jet may be used for external wall. Contaminants, dust and foreign matter should be removed by cleaning with damped cloth. Oil or grease should be removed by solvent cleaning or mild detergent. Allow surface to dry again.

New cement floor

Moisture Content must be below 6% checked by Sovereign Moisture Meter. Foreign and unstable matter such as powder, dirt, dust, contaminants and loose plaster should be removed by low pressure water jet washing. Oil or grease should be removed by solvent cleaning or mild detergent. Allow surface to dry again.

Recommended No. of Coats	: 1 coat
Recommended Film Thickness per coat	: 20 microns for dry film 34 microns for wet film
Theoretical Coverage at Recommended Film Thickness	: $29 \text{ m}^2 / \text{liter}$ (for dry film thickness of 20 microns)

NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam
Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836346 – 3836349

 www.nipponpaint.com

NIPPON EP4 CLEAR SEALER

$$\text{Theoretical Coverage (m}^2 \text{ / liter)} = \frac{\text{Volume Solid (\%)} \times 10}{\text{Dry Film Thickness (\mu)}}$$

Practical Coverage (20% Loss Factor) : 23.2 m² / liter (for dry film thickness of 20 microns)

Note : This theoretical coverage rate has been calculated from the volume solid of the material and is related to the amount of coating applied onto a perfectly smooth surface without wastage. For a practical coverage rate, due allowance should be made for atmospheric conditions, surface roughness, geometry of the article being coated, the skill of applicator, method of application etc. when estimating quantities required for a particular job.

Application Data:

Application Methods	: Brush, roller, compressed air spray and airless spray		
Guiding Data for Spray	:	<u>Air</u>	<u>Airless</u>
	Delivery Pressure (kg/cm ²)	3 - 4	140 - 170
	Tip size at 60° angle	1.3 mm	0.015" - 0.017"
Thinning	:		
	Roller & Brush	40% maximum	
	Air Spray	40% maximum	
	Airless Spray	10% maximum	
Mixing Ratio	:	4 parts by volume of NIPPON EP4 CLEAR SEALER (BASE) to 1 part by volume of NIPPON EP4 HARDENER.	
		Stir the content of the BASE component, continue stirring and gradually add the total content of the HARDENER component, continue stirring until a homogeneous mix is obtained.	
Pot Life at 25°C to 30°C	:	4 - 6 hours after mixing, depending on prevailing temperature	

Thinner : NIPPON SA 65 THINNER

Cleaning Solvent : NIPPON SA 65 THINNER

Note: All equipment should be cleaned IMMEDIATELY with Thinner after use. For thinning, substitute thinners other than those approved or supplied by Nippon Paint may adversely affect the product performance and void product warranty whether expressed or implied.

Drying Time at 25°C to 30°C:

Dry to touch	:	1 - 2 hours
Dry to handle	:	16 hours
Dry to overcoat	:	Minimum 16 hours
Curing time at 25°C to 30°C	:	6 - 7 days

Note: Drying time will become remarkable under low temperature. Exposure of the paint film to water, chemical and abrasion

NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam
Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836346 – 3836349

www.nipponpaint.com

NIPPON EP4 CLEAR SEALER

should be avoided as far as possible before full cure of the coating. Allow the surface to dry thoroughly prior to overcoating.

Standard Packing : 5 Liters (4 Liters BASE & 1 Liter HARDENER)
20 Liters (16 Liters BASE & 4 Liters HARDENER)

Environmental Conditions during Application:

1. Do not apply when the relative humidity exceeds 85%. The temperature of the substrate to be painted must be 3°C higher than the dew point.
2. Do not apply at temperature below 7°C. If not, drying and overcoating time will be considerably extended.
3. During application of the paint, naked flame, welding operations and smoking should not be allowed and good ventilation is necessary.

Safety, Health and Environmental Information:

1. Flammable Liquid. Do not expose to heat, sparks or open flame.
2. Skin Contact: May cause moderate skin irritation. Avoid prolong contact with skin. Use solvent resistant glove. To remove splashes of paint from skin, use soap and water.
3. Inhalation: Respiratory irritation. Only used in well ventilated areas. Do not breathe vapor or spray paint. Respirator with organic vapor cartridges recommended.
4. Eye Contact: Cause severe eye irritation and blurred vision. Safety glasses / goggles with side shields recommended. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.
5. Ingestion: Harmful if swallowed. Keep away from drinks, food and out of reach of children. If swallowed, seek medical advice immediately and show the container or label.
6. In the event of an accident, contain and collect spillage using sand or earth or absorbent. Do not empty into drain or water courses.
7. Wastes and empty containers should be treated and disposed of in accordance with national and local regulations. Empty containers and packaging should be taken for recycling, recovery or disposal through a suitably qualified or licensed contractor.

NOTE: The information given applies to the product and its performance under specific test conditions. Due to the varied circumstances beyond our control under which the product may be applied, for specific application, please contact Nippon Paint Sales & Marketing Dept. We reserve the right to modify our product data sheet without further notice.

NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam
Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836346 – 3836349

www.nipponpaint.com