

Version No.: 4 Updated Date: 20.05.24

PRODUCT DATA SHEET

INTERIOR SEALER

	INTERIOR OF AFRICA AND A STATE OF
Description	INTERIOR SEAER is a water-based environmentally friendly product that is suitable for masonry surfaces. It is formulated to achieve better adhesion and improve the deterioration
	of emulsion paints by strong concentration of cement chemicals.
Туре	Modified Acrylic Emulsion
Uses	As sealer for Interior masonry surfaces in which a high degree of alkalinity is envisaged such as:
	- Cement plasters - Brickworks
	- Concrete - Gypsum board
Finish	Matt
	Colour: Standard White
Features	- Good alkaline resistance
	- Efflorescence resistance to prevent discolouration
	- Good adhesion
	- Fast-drying for convenient recoating
	- Easy to use
	- Environmentally friendly product
	- The product is particularly compatible with the finishing coat of high-end product system specialized for project.
	- Does not contain Lead, Mercury and heavy metals
	- Ultra-low VOCs (containing < 25g/L VOC, meeting the VOC requirement)
	- Product is GREENGUARD Gold certified, meeting LEED standards for Green buildings
	- Comply with National technical regulation QCVN 08:2020/BCT on the limits of Lead content in paints.
APPLICATION DATA	
Surface Preparation	Surface must be clean, dry, and stable.
	Suggested Treatment:
	Moisture: High moisture will cause paint defect. Observe the following level prior to painting:
	- Masonry: below 16% by Protimeter Mini BLD 2000 Moisture meter
	below 60% by Lutron MS-7003 Moisture meter
	All water seepage must be checked and repaired.

NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836349



INTERIOR SEALER

	<u>Unstable matter:</u> Powder, film, dirt, plaster etc. Remove by high pressure water jet wash or mechanical means such as power brush or scraper whichever is suitable.
	<u>Contaminants:</u> Dust and foreign matter must be removed by cleaning with damp cloth. Oil or grease should be removed by solvent cleaning or mild detergent. Allow surface to dry again.
	Algae/Fungus: Remove by chisel or scraper and treat with ANTI-FUNGUS SOLUTION. Rinse again with clean water and dry.
	Hairline cracks: Fill cracks with solvent-based filler or non-water soluble material.
Application Methods	Brush, roller or airless spray
Coverage	Theoretical: 8.8 - 11.7 m²/Liter (30 - 40 microns DFT)
Dilution	Use clean water
	Roller & brush - 20% maximum
	Airless Spray - 10% maximum
Spray Application	Airless Spray
	Delivery Pressure (kg/cm²) 120 - 150
	Tip size at 60° angle 0.017"
	Dilution 10% maximum
Recommended Film	30 - 40 microns DFT (Dry Film Thickness)
Thickness per coat	86 - 114 microns WFT (Wet Film Thickness)
Drying Time	Surface dry: 10 minutes at 30°C
Overcoating Time	2 hours. Minimum based on normal conditions.
Cleaning	Wash all equipment immediately after use with clean water
Storage	Keep containers tightly closed. Store in cool, dry and well-ventilated place at temperature between 5 to 40°C.
Packing	18 Liters Containers
Volume Solid (%)	35 ± 2
Precaution	Coverage depends on film thickness, roughness or porosity of the surface, loss during painting, etc.
	The actual drying time and time before recoating may be shorter or longer, depending on film thickness, temperature, ambient humidity, ventilation, etc.
	Avoid painting when the temperature is below 10°C and the humidity is over 85%. Avoid direct contact with sensitive skin. Use appropriate protective equipment.
NOTE	The information given applies to the product and its performance under specific test conditions. Due to the varied circumstances beyond our control under which the product may be applied, for specific application, please contact Nippon Paint Sales & Marketing Dept. We reserve the right to modify our product data sheet without further notice.

NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836349

