

Version No.: 3 Updated Date: 20.05.24

#### PRODUCT DATA SHEET

#### **MATEX LIGHT**

Type A multi-purpose Acrylic Copolymer Emulsion  Decorative and protective coat for interior surfaces such as: - Cement plasters - Brickworks - Gypsum boa - Concrete - Primed wood - Fiberboards  Finish Matt Colour: Wide range of attractive and modern colours.			
- Cement plasters - Brickworks - Gypsum boat - Concrete - Primed wood - Fiberboards  Finish Matt			
- Concrete - Primed wood - Fiberboards  Finish Matt			
Finish Matt			
Colour: Wide range of attractive and modern colours.			
	Colour: Wide range of attractive and modern colours.		
Features - Good hiding power			
- Good flow & leveling	- Good flow & leveling		
- Easy touch-up	- Easy touch-up		
- Anti-fungus properties			
- Does not contain Lead, Mercury and heavy metals			
- Ultra-low VOCs (containing < 25g/L VOC, meeting the VOC requirement)			
- Green Label Certificate			
- Comply with National technical regulation QCVN 08:2020/BCT on the limits Lead content in paints.	of EIRING 21-22		
APPLICATION DATA			
Surface Preparation Surface must be clean, dry, and stable.	Surface must be clean, dry, and stable.		
Suggested Treatment:	Suggested Treatment:		
<u>Dirt/Powder:</u> Clean with damp cloth and remove loose powder. Mild detergused.	jent may be		
Old Paint/Plaster/Skimcoat: Unstable old film / substrate should be remove scraper, power grinder whichever is appropriate. Uneven substrates must be with an approved putty / skimcoat.	•		
Moisture: High moisture will cause paint defect. Observe the following le painting:	evel prior to		
- Masonry: below 16% by Protimeter Mini BLD 2000 Moisture meter	- Masonry: below 16% by Protimeter Mini BLD 2000 Moisture meter		
below 60% by Lutron MS-7003 Moisture meter			
All water seepage must be checked and repaired.			

## NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836349



## **MATEX LIGHT**

	Algae/Fungus: Remove by chisel or scraper and treat with ANTI- FUNGUS SOLUTION. Rinse again with clean water and dry.		
	Oil/Grease: Clean off with mild detergent and a little solvent if necessary. Wash thoroughly to remove all trace.		
Application Methods	Brush, roller or airless spray		
Coverage	Theoretical: 8.8 - 11.7 m <sup>2</sup> /liter (30 - 40 microns DFT)		
Dilution	Use clean water		
	Roller & brush	- 20% maximum	
	Airless Spray	- 10% maximum	
Spray Application		Airless Spray	
	Delivery Pressure (kg/cm²)	120 - 150	
	Tip size at 60° angle	0.017"	
	Dilution	10% maximum	
Recommended	- 1 - 2 coats INTERIOR SKIMCOAT		
Painting System	- 1 coat INTERIOR SEALER		
	- 2 coats MATEX LIGHT		
Recommended Film	30 - 40 microns DFT (Dry Film Thickness) 86 - 114 microns WFT (Wet Film Thickness)		
Thickness per coat			
Drying Time	Surface dry: 10 minutes at 30°C		
Overcoating Time	2 hours. Minimum based on normal conditions.		
Cleaning	Wash all equipment immediately after use with clean water		
Storage	Keep containers tightly closed. Store in cool, dry and well-ventilated place at temperature between 5 to 40°C.		
Packing	18 Liters Containers		
Volume Solid (%)	35 ± 2		
Precaution	Coverage depends on film thickness, roughness or porosity of the surface, loss during painting, etc.		
	The actual drying time and time before recoating may be shorter or longer, depending on film thickness, temperature, ambient humidity, ventilation, etc.		
	Avoid painting when the temperature is below 10°C and the humidity is over 85%. Avoid direct contact with sensitive skin. Use appropriate protective equipment.		
NOTE	The information given applies to the product and its performance under specific test conditions. Due to the varied circumstances beyond our control under which the product may be applied, for specific application, please contact Nippon Paint Sales & Marketing Dept. We reserve the right to modify our product data sheet without further notice.		

# NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836349

