

Version No.: 5 Updated Date: 20.05.24

### PRODUCT DATA SHEET

### **WEATHERBOND SEALER**

Description	WEATHERBOND SEALER is based on latest Nano technology containing a superior nanocomposite binder specially formulated for external masonry surfaces. It forms a multi Titanium laminar film that prevents efflorescence and degradation of finishing coats caused by strong cement alkali.		
Туре	Modified Acrylic Nano Polymer Emulsion		
Uses	As sealer used for exterior surfaces such as:		
	- Cement plasters - Concrete - Brickworks		
Finish	Sheen Colour: Standard White		
Features	- Excellent alkali resistance - Excellent efflorescence resistance to prevent discolouration		
	- Good adhesion on recommended surfaces		
	- Anti-Fungus and Algae resistance property		
	- Easy to use		
	- The product is particularly compatible with the finishing coat of high-end product system specialized for project.		
	- Does not contain Lead, Mercury and heavy metals		
	- Low VOCs (containing < 50g/L VOC, meeting the VOC requirement)		
	- Product is GREENGUARD Gold certified, meeting LEED standards for Green buildings		
	- Comply with National technical regulation QCVN 08:2020/BCT on the limits of Lead content in paints.		
APPLICATION DATA			
Surface Preparation	Surface must be clean, dry, and stable.  Suggested Treatment:  Moisture: High moisture will cause paint defect. Observe the following level prior to		
	painting:		
	- Masonry: below 16% by Protimeter Mini BLD 2000 Moisture meter		
	below 60% by Lutron MS-7003 Moisture meter		
	All water seepage must be checked and repaired. <u>Unstable matter:</u> Powder, film, dirt, plaster etc. Remove by high pressure water jet wash or mechanical means such as power brush or scraper whichever is suitable. <u>Contaminants:</u> Dust and foreign matter must be removed by cleaning with damp cloth. Oil		

## NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836349



# **WEATHERBOND SEALER**

	or grease should be removed by solvent cleaning or mild detergent. Allow surface to dry again.		
	Algae/Fungus: Wash off and treat with ANTI-FUNGUS SOLUTION. Rinse again with clean water and dry.  Hairline cracks: Fill cracks with solvent-based filler or non-water soluble material.		
Application Methods	Brush, roller or airless spray		
Coverage	Theoretical: 9.0 – 12.0 m²/Liter (30 - 40 microns DFT)		
Dilution	Use clean water		
	Roller & brush	- 20% maximum	
	Airless Spray	- 10% maximum	
Spray Application		Airless Spray	
	Delivery Pressure (kg/cm²)	120 - 150	
	Tip size at 60° angle	0.017"	
	Dilution	10% maximum	
Recommended Film	30 - 40 microns DFT (Dry Film Thickness) 83 - 111 microns WFT (Wet Film Thickness)		
Thickness per coat			
Drying Time	Surface dry: 20 minutes at 30°C		
Overcoating Time	2 hours. Minimum based on normal conditions.		
Cleaning	Wash all equipment immediately after use with clean water		
Storage	Keep containers tightly closed. Store in cool, dry and well-ventilated place at temperature between 5 to 40°C.		
Packing	18 Liters Containers		
Volume Solid (%)	36 ± 2		
Precaution	Coverage depends on film thickness, roughness or porosity of the surface, loss during painting, etc.		
	The actual drying time and time before recoating may be shorter or longer, depending on film thickness, temperature, ambient humidity, ventilation, etc.		
	Avoid painting when the temperature is below 10°C and the humidity is over 85%. Avoid direct contact with sensitive skin. Use appropriate protective equipment.		
NOTE	The information given applies to the product and its performance under specific test conditions. Due to the varied circumstances beyond our control under which the product may be applied, for specific application, please contact Nippon Paint Sales & Marketing Dept. We reserve the right to modify our product data sheet without further notice.		

# NIPPON PAINT (VIETNAM) CO., LTD

No. 14, 3A Road, Bien Hoa Industrial Zone II, Long Binh Tan Ward, Bien Hoa City, Dong Nai Province, Vietnam Tel: (84).251.3836579 – 3836586 (8 lines), Fax: (84).251.3836349

